

ACTH-201 氯化橡胶防腐底漆(铁红)

ACTH-201 Chlorinated Rubber Anticorrosive Primer (Iron red)

产品特性 极好的防腐防锈性能、耐海水性、干燥迅速 Excellent anticorrosive and rust property and seawater resistance, quick drying. 同各类底材附着力良好

Good adhesion to all kinds substrates

覆涂氯化橡胶面漆防腐效果甚佳,在-20℃仍可施工

Wonderful effect with Chlorination Rubber Anticorrosive Finish. Application can be performed at

-20℃.

产 品 用 途 主要用于新船或旧船水线以下及以上部位的防锈涂层。

Uses As an antirust paint for the lower and upper part of waterline of new or existing ships.

颜 色 铁红、灰 Color Iron red or gray

施工条件 无气喷涂 Airless spray 推荐 Recommended

Application method 喷嘴尺寸 Nozzle tip 0.4~0.5mm 压力 Fluid pressure 100~150kg/cm²

稀释比率 Thinning ratio 0~5% by weight (重量比)

适用于常规的喷涂、刷涂和辊涂

May be applied by spray, brush, or roller.

稀释剂 氯化橡胶稀释剂
Thinner Chlorinated rubber thinner

混 合 比 率 单组分

涂 装 膜 厚 干膜: 50μm/道 湿膜:100μm/道

One-pack

Film thickness Dry film thickness: 50µm/coat Wet film thickness:100µm/coat

固体含量 58% Solid content

Mixing ratio

比重 1.38 Specific gravity

涂 覆 率 理论值:0. 11 千克/平方米/50μm 0.087L/平方米/50μm Coverage rate Theoretical:0.11kg/m²/50μm 0.087L/m²/50μm

实际值:与表面处理,外界环境,施工方法等多种因素有关。

Actual: depending on the surface treatment, environment and application methods.

干燥时间 温度 10° 20° 30° Drying time Temperature

指触干燥 30mins 20mins 15mins



	100	2 2 2 3 10	
ı	¥5.	臣巴	
ı	100	4000	1
ш	FI	XI	

_	Dry to touch			_			
	实干:	5hrs	3.5hrs	3hrs			
	ティ: Dry to handle	31115	5.51118	31118			
	Dry to fiancie						
涂装间隔	Min. 最小	5hrs	3.5hrs	3hrs			
Coating interval	Max. 最大			_			
储存期限	一年						
Shelf life	,						
	12 months						
包装规格	单组份包装: 20kg/桶						
Packing specification 表面处理	One-component packing: 20 kg/barrel 用清水冲去盐分以及其它水溶性污物。						
表面处理 Surface preparation	用有水冲去益力以及其它水谷性污物。 Remove salt and other water-soluble contaminants with flesh water.						
	依照 SSPC-SP1 溶剂清洗标准除去油脂。						
	Remove oil thoroughly with suitable detergent in accordance with SSPC-SP1						
	除去焊接飞溅并处理焊缝、毛刺使其光顺						
	Remove weld spatter and w						
	•			到 ISO Sa2.5(SSPC-SP10)。或用电动工具			
	处理表面达到 ISO St3.0						
	All damaged shop primer, rust and scale should be thoroughly cleaned by abrasive blasting to Sa2½						
	or power tool cleaning to ISO St3.0.						
	用高压空气吹扫除去灰尘等污物。						
	Remove dust and dirt by high-pressure air before paint application.						
	施工前确认表面清洁干燥。						
	Confirm the surface clean a	and dry before a	oplication.				
涂装配套	适用底材:裸钢或旧漆膜						
Coating system	Substrate: bare steel or the surfaces with old paint film.						
	适用上涂: 乙烯链接漆、氯化橡胶水线漆、氯化橡胶防腐面漆或参考我公司的配套。						
	Subsequent coats: Vinyl Tie Coat, Chlorinated Rubber Boot Topping Paint, Chlorinated Rubber						
	Anticorrosive Finish, or refer to our coating system.						
安全注意事项	任何油漆施工中均应保证提供以下措施:						
Safety Precautions	The following be guarantee	ed during any pa	int application	ons:			
	避免接触皮肤和眼睛。						
	Avoid skin and eye contact. 如果油漆接触到皮肤或眼睛,应用大量水冲洗并立即就医。						
	如果沺漆接触到皮肤或眼睛,应用天重水冲洗升立即就医。 In case of skin or eye contact, flush with large amount of water and immediately get medical						
	attention.	ontact, musii wi	ui iaige aiii	doubt of water and immediately get medical			
	保证良好的通风。						
	Assure well-ventilated wor	king place					
	小心火灾或爆炸。	amg place.					
	Take precautions of the risk	cs of fire or expl	osion				
	现场遵守一切健康安全规	-					
	Observe all health and safe		ı site				
提醒注意	本说明书所提供信息均为目前我方所掌握最全面正确的资料,鉴于产品使用条件非我方所能控						
Declaration				负责。由于我公司产品及生产工艺的不断发			
	展,此中所有信息均以我方确认为准。						
	The information given on this technical data sheet is correct to the best of our knowledge. In						
				ct are beyond our control, so no guarantee is			
	involved herein, namely, we are responsible for the buyers only in terms of their selecting a product.						
	involved herein, namely, w	e are responsible	e for the buy	ers only in terms of their selecting a product.			
				ers only in terms of their selecting a product. f the constantly improvement of our product			