

FXT02-3 隔热面漆

FXT02-3 Heat Insulating Finish

产品特性 Characteristics	漆膜坚固、耐磨、对太阳的热辐射有很好的反射效果; Firm Paint film with abrasion resistance, and good reflection to solar radiation. 良好的施工性能; Good application property 良好的保光、保色、耐候性。 Good color and gloss retention, and good weather resistance.					
产 品 用 途 Uses	适用于石油化工行业的各类球罐、管道的外壁隔热防腐。 An exterior insulating and anticorrosive coating for all kinds of spherical tanks in petrochemical industry and pipelines.					
颜 色 Color	白色及各色 White and all colors					
施 工 条 件 Application method	无气喷涂 Airless spray 推荐 Recommended 喷嘴尺寸 Nozzle tip 0.5~0.6mm					
	压力 Fluid pressure 150kg/cm²					
	稀释比率 Thinning ratio 0~5% 适用于无气喷涂、空气喷涂、刷涂及辊涂。 May be applied by airless spray, air spray, brush, or roller.					
稀释剂 Thinner	专用稀释剂 Special thinner					
混合比率 mixing ratio	主剂/固化剂=7/1(重量比) Base/hardener=7/1(by wt)					
混合使用期 Pot life	温 度 ($^{\circ}$ C): 10° C 20° C 30° C Temperature ($^{\circ}$ C): 混合使用期 (hrs): 10 8 6 Pot life (hrs):					
涂 装 膜 厚 Film thickness	干膜: 30μm/道 湿膜: 55μm/道 Dry film thickness:30μm /coat Wet film thickness:55μm s/coat					
固体含量 Solid content	63%					
比重 Specific gravity	1.2					



·	THE 1/4 to 101 /m²/20	0.075	II. / ² /2 O				
涂覆率 Common meta	理论值:0.10kg/m²/30μm	·					
Coverage rate	- ·	Theoretical: 0.10kg/m²/30μm 0.077L/m²/30μm					
	实际值:与表面处理,外界环境,施工方法等多种因素有关。 Actual: depending on the surface treatment, environment and application methods.						
	return depending on the surface	e treatment, e	iiviioiiiiieii t	та аррпес	ation methods.		
干燥时间	温度(℃)	10	20	30			
Drying time	Temperature ($^{\circ}$ C)						
	指触干燥(hrs)	2	1.5	1			
	Dry to touch (hrs)						
	半硬干燥(hrs)	24	12	8			
	Dry hard (hrs)						
涂装间隔							
Coating interval	Min. 最小(hrs)	24	12	8			
	Max. 最大 (day)						
储存期限	一年						
Shelf life	12 months						
包装规格	22.8kg/组 组份一为 20kg, 组份二为 2.8kg。						
Packing specification	A kit 22.8 contains Part A 20kg and Part B 2.8kg.						
表面处理	应 漆武山	- 編 - 法 - 法	五姓霉.				
Surface preparation	底漆或中层漆表面必须彻底干燥、清洁、无结露; The primer or intermediate coat surface must be dry, clean and free of dew.						
Surface proparation	施工前请注意与底漆或中层漆的涂装间隔。						
	Please note the coating interval	to the primer	or intermedia	ate coat be	fore application.		
适用下涂	环氧隔热底漆,环氧隔热中层漆。						
Primer coat:	Epoxy Heat Insulating Primer and Epoxy Heat Insulating Intermediate Coat						
安全注意事项	任何油漆施工中均应保证提供以下措施:						
Safety Precautions	The following shall be guaranteed during any paint applications: 避免接触皮肤和眼睛。						
	Avoid skin and eye contact.						
	如果油漆接触到皮肤或眼睛,应用大量水冲洗并立即就医。						
	In case of skin or eye contact, flush with large amount of water and immediately get medical						
	attention.						
	保证良好的通风。						
	Assure well-ventilated working place. 小心火灾或爆炸。						
	小心久天以寒炸。 Take precautions of the risks of fire or explosion.						
	现场遵守一切健康安全规定。						
	Observe all health and safety regulations on site.						
提醒注意 本说明书所提供信息均为目前我方所掌握最全面正确的资料,鉴于产品使用条							
Declaration	制,此中信息不含担保,即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发						
	展,此中所有信息均以我方确认为准。						
	The information given on this technical data sheet is correct to the best of our knowledge. In						
	consideration of the application conditions of the product are beyond our control, so no guarantee is						
	involved herein, namely, we are responsible for the buyers only in terms of their selecting a product. All data must be clarified from our company because of the constantly improvement of our product						
	and its manufacturing process.	company	. Jeanse Of th	- Constant			

