

FXT02-1 隔热底漆

FXT02-1 Heat Insulating Primer

产品特性 Characteristics	极佳的防锈性能、漆膜坚固 Excellent antirust property with firm paint film 附着力极佳、耐磨损、物理机械性能优异。 Excellent adhesion, abrasion resistance and physical and mechanical properties.
产品用途	适用于钢材、储气罐外壁防腐,作为底漆使用。
Uses	An anticorrosive primer for steel and exterior of air storage tank.
颜 色	灰色
Color	Gray
施工条件 Application method	无气喷涂 Airless spray 推荐 Recommended
	喷嘴尺寸 Nozzle tip 0.5~0.6mm
	压力 Fluid pressure 150kg/cm²
	稀释比率 Thinning ratio 0~5%
	适用于无气喷涂、空气喷涂、刷涂及辊涂。
	May be applied by airless spray, air spray, brush, or roller.
稀释剂	专用稀释剂
Thinner	Special thinner
混合比率	主剂/固化剂=8/1(重量比)
Mixing ratio	Base/hardener=8/1(by wt)
混合使用期	温 度 (℃): 10℃ 20℃ 30℃
Pot life	Temperature ($^{\circ}$ C):
	混合使用期 (hrs): 10 8 6
	Pot life (hrs):
涂装膜厚	干膜: 50μm/道 湿膜: 85μm/道
Film thickness	Dry film thickness:50μm /coat Wet film thickness:85μm /coat
固体含量	68.5%
Solid content	
比重	1.45
Specific gravity	
涂覆率	理论值:0.12kg/m²/50μm 0.088L/m²/50μm
Coverage rate	Theoretical: 0.12kg/m²/50μm 0.088L/m²/50μm



	实际值:与表面处理, 外界环境, 施工方法等多种因素有关。
	Actual: depending on the surface treatment, environment and application methods.
干燥时间	温度 (℃) 10 20 30
Drying time	Temperature (°C)
	指触干燥(hrs) 2.2 1.7 1.2
	Dry to touch (hrs)
	半硬干燥(hrs) 16 11 9
	Dry hard (hrs)
 涂装间隔	
Coating interval	Min. 最小 (hrs) 16 11 9
	Max. 最大 (day)
储存期限	一年
Shelf life	12 months
包装规格	22.5kg/组 组份一为 20kg,组份二为 2.5kg。
Packing specification	A kit 22.5kg contains Part A 20kg and Part B 2.5kg.
表面处理	用喷砂除锈方式除去铁锈和氧化皮达到 ISO Sa2.5 级或用电动工具处理表面达到 St3 级。
Surface preparation	Rust and oxide layer should be thoroughly cleaned by abrasive blasting to ISO Sa2.5 or power to
	cleaning to St3.
适用底材	裸钢
Substrate:	Bare steel
适用上涂	隔热中层漆、隔热面漆
Top coat:	Heat Insulating Intermediate Coat and Heat Insulating Finish.
安全注意事项 Safety Precautions	任何油漆施工中均应保证提供以下措施:
	The following shall be guaranteed during any paint applications: 避免接触皮肤和眼睛。
	Avoid skin and eye contact.
	如果油漆接触到皮肤或眼睛,应用大量水冲洗并立即就医。
	In case of skin or eye contact, flush with large amount of water and immediately get medic
	attention.
	保证良好的通风。
	Assure well-ventilated working place. 小心火灾或爆炸。
	Take precautions of the risks of fire or explosion.
	现场遵守一切健康安全规定。
	Observe all health and safety regulations on site.
提醒注意	本说明书所提供信息均为目前我方所掌握最全面正确的资料,鉴于产品使用条件非我方所能抗
Declaration	制,此中信息不含担保,即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展,此中所有信息均以我方确认为准。
	The information given on this technical data sheet is correct to the best of our knowledge. In
	consideration of the application conditions of the product are beyond our control, so no guarantee is
	involved herein, namely, we are responsible for the buyers only in terms of their selecting a product.
	A11 1 / / 1 1 1 C 1 C 1 / / / / / / / / /
	All data must be clarified from our company because of the constantly improvement of our product and its manufacturing process.